DAKOTATM TECHNICAL DATA SHEET Rev: 29 August, 2022

DIFU STOP 140



INDEX

- 1. Code Registry
- 2. Description
- 3. Use
- 4. Features
- 5. Technical specification

1. CODE REGISTRY

Code	Description	Dimensions (m)	Weight	Colour	Pkg. / Pallet
LUC70-9052	Difu Stop 140	1,50 x 50	140 gr/m²	Grey	75 m² / 24 rolls
MATERIAL	Made of PP (polypropylene) and PE (polyethylene) w	vith high protection to U	V rays.		

Made of PP (polypropylene) and PE (polyethylene) with high protection to UV rays.

DESCRIPTION	METHOD	UNIT	NOMINAL VALUE	TOLLERANCE (min/max)		
Reaction to fire	EN 13501-1 EN 11925-2	[class]	E	-	-	
Water resistance	EN 1928	-	Conforming	-	-	
Water vapour transmission properties (S _d)	EN 1931	[m]	20	-10	+10	
Maximum longitudinal/transverse tensile strength	EN 12311-1 EN 13859-1	[N/5cm MD/CMD]	>250/>180	-	-	
Longitudinal/transverse elongation	EN 12311-12 EN 13859-1	[%]	>50/>50	-	-	
Longitudinal/transverse tear strength	EN 12310-12 EN 13859-1	[N]	>65/>65	-	-	
Impact resistance	EN 12691	-	npd	-	-	
Joint strength	EN 12317-2	[N]	npd	-	-	
Resistance to deformation under load	EN 13984	-	npd	-	-	
Resistance to alkali	EN 13984 EN 12311-2	-	npd	-	-	
Durability of water vapour resistance against ageing	EN 1296 EN 1931	-	conforming	-	-	
Dangerous substance	-	-	npd	-	-	

2. DESCRIPTION

Water vapour berrier for roofing (tale and stale roofs), for the inclined ventilated roofs, fora a case when the insulation is the ceiling and between roof beams or underneath them. The water vapour barrier needs to be installed with reccomended overlap.

This product does not contain any dangerous substances





DIFU STOP 140

3. USE

Used to protect against infiltration of water, air and wind. It guarantees correct breathability, optimizing the insulation features.

4. FEATURES

- · Airtightness.
- Low water vapor permeability.
- Avoids dew point formation in insulation.
- In addition:
- Ensures the durability and effectiveness of the insulation.
- Suppression of condensation risks.
- Reduction of thermal bridges.
- Healthy rooms thanks to "breathing" walls.
 Ensures dryness of insulation and wood structures.
- Ideal for all types of insulation.
- · Allows the migration of water vapor present in the insulation to the interior of the premises.

5. TECHNICAL SPECIFICATION

Specification	Description	Unity	Price
Dak.R.LUC70.9052	Supply and installation of 3-layers vapour barrier, which comprises of 2 layers of non-woven polypropylene spunbond with special monolithic coating and 1 vapour barrier. Rolls = 1,50 x 50 m. Single packed in cellophane tape. Made of PP (polypropylene). Good-practice workmanship using our system products improves thermal insulation performances while avoiding any potential humidity and condensation damage. It protects against infiltration of water, air and wind.	roll	-

This data sheet supersedes and replaces all previous ones. The information contained herein is accurate to our present knowledge. Dakota Group S.a.S. assumes no responsibility or liability with respect to the information given. Dakota Group S.a.S. reserves the right to change speci cations and models without prior notice. Dakota Group S.a.S. - Via Don Cesare Scala, 55 - Brentino Belluno (VR) - Italy - tel. 045-6284080 - fax. 045-6284075 www.dakota.eu - info@dakota.eu o u cio.tecnico@dakota.eu